CONDOR

WESTFÄLISCHE DRAHTINDUSTRIE GmbH
DRAHT- UND SEILWERKE ROTHENBURG
Friedensstr. 21 D-08429 Rothenburg/Sachs
Telefon (03491) 110 - Telefax (03491) 1206

conductor data sheet

material (abbreviation):	**ACSR**		
identification:	**402/52**		
standards:	**EN 50182 CONDOR**	valid since:	**1 / 2005**

mechanical datas

conductor cross section:	**454,5**	mm^2	max. permissible strain:	-	N /mm^2
relation number of cross sections:	-		mean permissible strain (EDS):	-	N /mm^2
conductor diameter:	**27,7**	mm	continious strain:	-	N /mm^2
weight:	**1530,8**	kg / km	thermal elongation coefficient:	**19,3**	10^-6/K
calculated breaking load:	**123,75**	kN	module of elasticity:	**70**	kN /mm^2
cross section related weight of length:	-	N/m*mm^2			

electrical datas

DC-resistance at 20°C :	**0,0719**	Ohm / km
conductivity at 20°C:	**35,38**	m / Ohm*mm^2
calculation factor of resistance:	**0,1894**	
coefficient of temperature:	**0,004**	1 / K
max. continious current load according to Webs:	-	A
up to 60 Hz by max. permissible conductor temperature ambient temperature 35°C; solar heating 900 W/m^2; wind velocity 0,6 m/s		

datas of construction

number of covering wires:	**54**		number of core wires:	**7**	
diameter of covering wires:	**3,08**	mm	core wires diameter:	**3,08**	mm
number of covering layers:	**3**		core diameter:	**9,24**	mm
covering cross section:	**402,3**	mm^2	core cross section:	**52,2**	mm^2

additional datas:

angle of max. oscillation:	**44,35**	°
according to VDE 0210;12/85 up to 200 m fieldlength ; q = 0,53 kN/m^2		
max. permissible continious conductor temperature:	**80**	°C

note : **greased Case 1**

S. Tygesen Energi A/s
Leverandør til energi- entreprenør og telesektoren
Strandvangen 33 · 5300 Kerteminde · +45 65 32 43 80 · www.tygesen-energi.dk